

LISTING OF THE CLAIMS

1. – 18. (canceled)

19. – 38. (canceled)

39. (currently amended) A tool made by a process comprising the steps of:

- a) combining an epoxide resin, an isocyanate resin, and a ~~bulk~~ filler to provide a resin mixture;
- b) adding a mixture of an tertiary amine and a cyclic amine to said resin mixture, said amines initiating a reaction between said epoxide resin and said isocyanate resin to form a polymer gel;
- c) dispensing said polymer gel into a mold;
- d) curing the polymer gel at a temperature of about 65°C to provide a polyisocyanurate foam member;
- e) cooling said mold and de-molding said polyisocyanurate foam member;
- f) post-curing the polyisocyanurate foam member by re-heating the polyisocyanurate foam member step-wise to a temperature of about 200°C; and
- g) cooling said post-cured polyisocyanurate foam member to room temperature to provide a post-cured polyisocyanurate foam tool capable of sustaining prolonged exposure to temperatures up to about 200°C while also maintaining ~~[[a]]an average~~ mechanical compressive strength of ~~at least 60% of a~~ mechanical compressive strength measured at room temperature about 25 MPa.

40. (original) The tool of claim 39, wherein said isocyanate resin comprises a mixture of diphenylmethane diisocyanate, methylene bisphenyl isocyanate, and polymethylene polyphenyl isocyanate.

41. (previously presented) The tool of claim 39, wherein said epoxide resin is resin formed by condensation reaction between a mixture of bisphenol A and epichlorohydrin resins or a mixture of bisphenol F and epichlorohydrin resins.

42. (original) The tool of claim 41, wherein the quantity of epoxide resin further comprises up to about 50 weight percent of a carboxyl-terminated butadiene acrylonitrile polymer.

43. (original) The tool of claim 39, wherein the tertiary amine is 2,4,6-tris(dimethylaminomethyl)phenol.

44. (original) The tool of claim 43, wherein the cyclic amine is N,N-dimethylcyclohexylamine.

45. (original) The tool of claim 39, wherein said quantities of said tertiary amine and said cyclic amine are in a ratio amount equal to about 2:1 to about 2.8:1 of tertiary to cyclic amine, and wherein the total quantity of amine is equal to about 0.5% to about 0.7% of said quantity of said isocyanate resin.

46. (original) The tool of claim 39, wherein the quantity of epoxide resin is about 51% to about 56% of said quantity of isocyanate resin.

47. (original) The tool of claim 39, wherein said epoxide resin and said isocyanate resin are present in a ratio amount of about 1:1.8 to about 1:2 of epoxide resin to isocyanate resin.

48. (original) The tool of claim **39**, wherein the isocyanate resin is present in an amount of about 60 weight percent to about 65 weight percent of said epoxide resin, said isocyanate resin, and said tertiary and cyclic amines.

49. (original) The tool of claim **39**, wherein said step of combining said epoxide resin and said isocyanate resin further includes adding a quantity of a surface active agent.

50. (original) The tool of claim **49**, wherein the surface active agent is present in an amount of about 2 weight percent to about 5 weight percent of said epoxide resin, said isocyanate resin, and said tertiary and cyclic amines.

51. (currently amended) The tool of claim **39**, wherein the step of combining further comprises incorporating said resin mixture and said ~~bulk~~ filler for about 1 minute.

52. (currently amended) The tool of claim **51**, wherein the ~~bulk~~-filler is present in an amount of about 10 weight percent to about 15 weight percent of said epoxide resin, said isocyanate resin, and said tertiary and cyclic amines.

53. (currently amended) The tool of claim **52**, wherein the ~~bulk~~-filler is selected from the list consisting of glass microspheres, glass-ceramic cenospheres, multi-cellular glass microspheres, polymeric microspheres, and comminuted form of silicon dioxide, mica, and beta eucryptite, and combinations thereof.

54. (currently amended) The tool of claim **53**, wherein the ~~bulk~~-filler further comprises fibers selected from the list consisting of fibers such as carbon fibers, e-glass, s-glass, and aramid fibers, and combinations thereof.

55. (currently amended) The tool of claim **51**, wherein the ~~bulk~~-filler is present in an amount of about 10 weight percent to about 15 weight percent of said epoxide resin, said isocyanate resin, and said tertiary and cyclic amines.

56. (original) The tool of claim **39**, wherein said step of combining said epoxide resin and said isocyanate resin further includes adding a quantity of water.

57. (original) The tool of claim **39**, wherein the step of post-curing further comprises the step of increasing the temperature of said cured foam member to 200°C over a period of at least about 36 hours.

58. (previously presented) The tool of claim **57**, wherein the step of increasing said temperature further comprises the steps of:

- a) heating the cured foam member to about 65°C for about 2 hours;
- b) increasing the temperature of the cured foam member up to about 150°C over about 8 hours and holding the temperature of the cured foam member at about 150°C for an additional 5 hours;
- c) increasing the temperature of the cured foam member to about 180°C over about 8 hours and holding the temperature of the cured foam member at about 180°C for an additional 5 hours;

- d) increasing the temperature of the cured foam member to about 200°C over about 5 hours and holding the temperature of the cured foam member at about 200°C for an additional 5 hours;
- e) decreasing the temperature of the cured foam member to about 65°C over about 5 hours and holding the temperature of the cured foam member at about 65°C for an additional 1 hour; and
- f) cooling the temperature of the cured foam member to room temperature.

59. (original) The tool of claim 58, further including the step of milling or shaping one or more surfaces to provide a 3-dimensional tool contour.

60. – 63. (canceled)

64. (currently amended) A tool made by a process comprising the steps of:

- a) combining an epoxide resin, an isocyanate resin, and a bulk filler to provide a resin mixture;
- b) adding a mixture of a tertiary amine and a cyclic amine to said resin mixture, said amines initiating a reaction between said epoxide resin and said isocyanate resin to form a polymer gel;
- c) applying said polymer gel onto a surface;
- d) curing the polymer gel at a temperature of about 65°C to provide a polyisocyanurate foam layer;
- e) cooling said polyisocyanurate foam layer;
- f) post-curing the polyisocyanurate foam layer by re-heating the polyisocyanurate foam member step-wise to a temperature of about 200°C; and
- g) cooling said post-cured polyisocyanurate foam layer to room temperature, to provide a foam tool capable of sustaining prolonged exposure to temperatures

up to about 200°C while also maintaining ~~[[a]]~~an average mechanical compressive strength of ~~at least 60% of a mechanical compressive strength measured at room temperature~~ about 25 MPa.

65. (original) The tool of claim **64**, wherein the step of applying further comprises spraying said foam gel onto said surface.

66. (currently amended) A high temperature insulation medium ~~comprising the light weight polyisocyanurate foam structure of claim 12~~ made by the process of claim 39.

67. (canceled)